

Antiferromagnetic vortex state in a high-temperature superconductor

B. Lake*, H. M. Rønnow†, N. B. Christensen‡, G. Aeppli§‡, K. Lefmann‡, D. F. McMorrow‡, P. Vorderwisch||, P. Smeibidl||, N. Mangkorntong¶, T. Sasagawa¶, M. Nohara¶, H. Takagi¶, T. E.

Mason#.

*Oak Ridge National Laboratory, P.O. Box 2008 MS 6430, Oak Ridge, TN 37831-6430, U.S.A.

†CEA (MDN/SPSMS/DRFMC), 17 Av. des Martyrs, 38054 Grenoble cedex 9, France.

‡Materials Research Department, Risø National Laboratory, 4000 Roskilde, Denmark.

§NEC Research Institute, 4 Independence Way, Princeton, New Jersey 08540-6634, USA.

||BENSC, Hahn-Meitner Institut, Glienicker Strasse 100, 14109 Berlin, Germany.

¶Department of Advanced Materials Science, Graduate School of Frontier Sciences, University of Tokyo, Hongo 7-3-1, Bunkyo-ku, Tokyo 113-8656, Japan.

#Experimental Facilities Division, Spallation Neutron Source, 701 Scarboro Road, Oak Ridge, TN 37830, U.S.A.

Magnetic fields penetrate conventional superconductors via normal state metallic inclusions, or vortices, which can exist in fluid or frozen states. At the macroscopic level, the phenomenology of high-temperature (high- T_c) superconductors follows this paradigm. However, at the microscopic level, vortices in high-temperature cuprates differ from those in conventional superconductors. Scanning tunneling microscopy indicates the persistence of an energy gap for electronic excitations in the vortex cores [1], and there are also predictions that the cores are magnetically ordered [2]. Recent experiments on $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ at optimal doping indicate that the individual vortices should be considered as nanomagnets with enhanced low frequency fluctuations but no static order [3]. Here we show that static, long-ranged, antiferromagnetism is associated with the vortex state in an underdoped sample.

La_2CuO_4 is an insulator with static commensurate antiferromagnetism. For $x > 0.05$, the magnetic correlations are characterized by incommensurate (IC) wavevectors of the type shown in the inset of fig. 1b [4]. Dynamic IC correlations are common to all metallic samples, and for $x \simeq 1/8$, they slow down to yield static order with a range in excess of 50 Cu-Cu spacings [5–7]. Our samples have $x = 0.10$ and develop superconductivity below a zero-field transition temperature of $T_c(H=0) = 29\text{K}$. The magnetotransport data in fig. 1a show that even a modest external magnetic field (H) strongly suppresses the onset of the zero-resistance state. Figure 1b displays the temperature (T)-dependence of the IC order, established via neutron diffraction. For $H=0$, the IC order is weak and T -independent up to at least 50K. A field of 5T produces a T -independent increase of $\sim 50\%$ in the signal above $T_c(H=0)$, similar to the enhancement reported at $T = 4.2\text{K}$ and $H = 10\text{T}$ for an $x = 0.12$ sample with $T_c(H=0) = 12\text{K}$ [8]. Our new finding is that between $T_c(H=0)$ and the irreversibility temperature $T_{\text{irr}}(H=5\text{T})$, a much stronger field-induced signal appears, saturating at over three times the zero-field signal.

A key to understanding our result is that the measured in-plane magnetic correlation length $\zeta \geq 600\text{\AA}$ is greater than both the superconducting coherence length $\xi \sim 20\text{\AA}$, and the $218\text{\AA}$ distance between vortices (at $H=5\text{T}$). The large value of ζ makes it unlikely that the antiferromagnetic signal arises from individual vortex cores, which have spatial extent ξ . The onset of the signal at a temperature in excess of $T_{\text{irr}}(H=5\text{T})$ is incompatible with interpretation of the irreversibility line as a vortex melting line, because vortex motion would dephase the IC order nucleated by the vortices. A more plausible account of our data proceeds from the hypothesis that the cores nucleate larger, immobile IC regions, which overlap both with each other and the pre-existing IC background to increase the IC volume fraction. Such agglomeration would occur as soon as the phase separation proposed by the theory of type II superconductors becomes advantageous, and leaves only small interstitial regions with SC phase coherence. Phase coherent superconductivity would then be established throughout the sample at the lower ‘irreversibility’ temperature via Josephson coupling between the finite-sized SC regions, rather than via freezing of a liquid of mobile vortices.

- [1] Renner, Ch., Revaz, B., Kadowaki, K., Maggio-Aprile, I. & Fischer, Ø. *Phys. Rev. Lett.* **80**, 3606-3609 (1998).
- [2] Arovas, D. P. Berlinsky, A. J. Kallin, C. & Zhang, S.-C. *Phys. Rev. Lett.* **79** 2871-2874 (1997).
- [3] Lake, B. *et al. Science* **291** 832-834 (2001).
- [4] Cheong, S.-W. *et al. Phys. Rev. Lett* **67**, 1791-1794 (1991).
- [5] Tranquada, J. M. Sternlieb, B. J. Axe, J. D. Nakamura, Y. & Uchida, S. *Nature* **375**, 561-563 (1995).
- [6] Suzuki, T. *et al. Phys. Rev. B* **57**, R3229-R3232 (1998);
- [7] Wakimoto, S. Birgeneau, R. J. Lee, Y. S. & Shirane, G. *cond-mat/0011392* (2000).
- [8] Katano, S. Sato, M. Yamada, K. Suzuki, T. & Fukase, T. *Phys. Rev. B* **62** R14677-R14680 (2000).

FIG. 1. Magnetotransport and neutron diffraction data for $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ as a function of temperature and magnetic field. Our sample was grown in an optical image furnace and has strontium content $x=0.10$, putting it in the underdoped superconducting regime with $T_c(H=0\text{T})=29\text{K}$. a) shows magnetotransport measurements parallel to the CuO_2 planes, obtained via a standard four-probe method; the colours indicate the electrical resistivity. In a magnetic field, the sharp transition from normal to superconducting states is broadened into a crossover region and vortices are thought to form at temperatures where the resistivity falls below its value at $T_c(H=0)$. Phase coherent superconductivity, characterised by zero resistance, sets in at the much lower ('irreversibility') temperature, $T_{\text{irr}}(H)$, marked by the white circles. b) shows the temperature-dependent intensity (above background) of the neutron diffraction signal for zero field (blue circles) and a field of 5T applied perpendicular to the CuO_2 layers (red squares). The lines are guides to the eye. Measurements were performed on a 1.5cm^3 sample, using the V2 triple-axis spectrometer at the Hahn-Meitner Institute, Berlin. The inset shows the relevant reciprocal space, labeled using the two-dimensional notation appropriate for the superconducting planes. The black circle at $(\frac{1}{2}, \frac{1}{2})$ represents the Bragg point associated with the commensurate antiferromagnetism of the insulating $x=0$ parent compound. The incommensurate antiferromagnetic order in our metallic $x=0.10$ material, gives rise to diffraction at the quartet of red circles $((\frac{1}{2}, \frac{1}{2}) + (0, \pm 0.12))$ and $(\frac{1}{2}, \frac{1}{2}) + (\pm 0.12, 0)$ where our measurements took place.

